



My Star land (LLC)

23 A Pryanishnikova, 127550, Moscow, Russia

Tel Fax: +7(495) 973-80-83

E-Mail: info@mystarland.com

NO	TISSUE PAPER PROPERTIES		UNIT		standard	minimum	Maximum	TEST METHOD
1	Basis Weight		gram/m ²		15	14.9	15.5	T 410 om 02
2	Thickness		micron	2 ply	90	85	100	T 411 om 05
3	Dry Tensile Strength	MD	grf/25.4 mm	2 ply	470	450	500	T 494 om 01
		CD			220	190		
4	Wet Tensile	MD	grf/25.4 mm	2 ply	100	95	110	T 456 om 03
5	Elongation	MD	%	2 ply	20	14	25	T 494 om 01
6	Brightness		%	2 ply	85	85	88	T 452 om 02

Tissue 15 GSM



My Star land (LLC)

23 A Pryanishnikova, 127550, Moscow, Russia
 Tel Fax: +7(495) 973-80-83
 E-Mail: info@mystarland.com

NO	TISSUE PAPER PROPERTIES		UNIT		standard	minimum	Maximum	TEST METHOD
1	Basis Weight		gram/m ²		16.5	16	16.7	T 410 om 02
2	Thickness		micron	2 ply	90	85	105	T 411 om 05
3	Dry Tensile Strength	MD	grf/25.4 mm	2 ply	550	450	650	T 494 om 01
		CD			250	200		
4	Wet Tensile	MD	grf/25.4 mm	2 ply	100	95	110	T 456 om 03
5	Elongation	MD	%	2 ply	20	14	24	T 494 om 01
6	Brightness		%	2 ply	85	85	87	T 452 om 02

Tissue 16 GSM



My Star land (LLC)

23 A Pryanishnikova, 127550, Moscow, Russia

Tel Fax: +7(495) 973-80-83

E-Mail: info@mystarland.com

NO	TISSUE PAPER PROPERTIES		UNIT		standard	minimum	Maximum	TEST METHOD
1	Basis Weight		gram/m ²		19	18.5	19.5	T 410 om 02
2	Thickness		micron	2 ply	100	90	110	T 411 om 05
3	Dry Tensile Strength	MD	grf/25.4 mm	2 ply	750	650	950	T 494 om 01
		CD			350	250		
4	Wet Tensile	MD	grf/25.4 mm	2 ply	100	95	110	T 456 om 03
5	Elongation	MD	%	2 ply	20	14	28	T 494 om 01
6	Brightness		%	2 ply	85	85	87	T 452 om 02

Tissue 19 GSM