



# My Star land (LLC)

23 A Pryanishnikova, 127550, Moscow, Russia  
Tel Fax: +7(495) 973-80-83  
E-Mail: [info@mystarland.com](mailto:info@mystarland.com)

## Softwood bleached sulphate pulp

Standard / ECF quality

## Quality Certificate

## Bleached Softwood Kraft Pulp (HP2high quality)

(The mechanical strength of the grinding in the mill CRA SR 60 oz)

Typical Physical Properties T220 SP-96				
Freeness	18	21	25	35
The absolute tear resistance	40	44	48	52
Burst Index	44	65	71	78
Breaking Length	7	7.8	10.6	11.2
Fracture strength (number of double folds)	800	1120	1200	1300

Physical Analysis	
Fiber Length Average	2.42 mm
Coarseness, mg/m	0.187
Ash	1.00

Physical Analysis	
Brightness, ISO	MIN86 - MAX88
Dirt Area, modified TAPPI ppm	<4.00
pH of the aqueous extract 5.0-7.0	5.0-7.0-6.3
bale weight	201kg
Bale size	450x600x800